Product Data Sheet – Headrow



Material	**Headrow Diamond Sawn Yorkstone.**
Description	Headrow is a sandstone from the coal measures of the Carboniferous age. It is a fine grained stone grey blue in colour with small darker deposits.
Country of Origin	UK

Test Properties - Summary

Water Absorption	4.3%	Slip Resistance	100 (Dry)
Flexural Strength	13.2 -14.6Mpa	Slip Resistance	92 (Wet)
Compressive Strength	104 -107 MN/m2	Apparent Density	2330 Kg/m3
Freeze Thaw Test	Failure due to frost action unlikely		

Please note: Sandstone is a natural product and all results are indicative and subject to variations.
Production tolerances expect +-2mm

Above Information is extracted from a Building Research Establishment Ltd (BRE) Report – Tests carried out December 2019

Aftercare

Natural stone can age gracefully with time. It is often considered that natural stone is at its best when mature, aged and naturally 'bedded in' to its environment. With this in mind you might consider leaving the stone in its natural form to allow time, use and the elements to impart the aesthetic that makes a natural product unique. On the other hand, consideration might be given to ways of maintaining the original, newly quarried form for as long as possible and also to safety such as reduced slip resistance from the build-up of organic growth.

Moss, Lichens Algae etc.

If you have concerns over reduced slip resistance due to the build-up of a green substance on your paving or setts then we suggest removal via a hosepipe or careful use of high pressure water jet. Green growth will usually appear in areas of low traffic and high planting, also in areas subject to damp and with little or no direct sunlight. The growth cannot be stopped entirely by applying a sealant as it can still grow on top of the sealant. Certain products such as moss inhibitors may alleviate the problem, careful use and application on test areas would be recommended

Stain Protection

If you wish to retain the newly quarried colouring of your natural stone and reduce the effect of natural ageing then you can apply products that will offer protection against staining. There are many products on the market offering various different properties. Be sure to conduct a thorough test sample prior to applying as some products can have an effect on colouring, appearance and slip resistance of the natural materials.

Cleaning

We suggest the best method of cleaning is to wash down with a hose pipe. Careful use a high pressure water jet if a more intensive clean is required being mindful not to wash out the aggregate or pointing that may be in the joints. We do not recommend the use of acid based cleaners due to their invasive actions. Discolouration will likely occur with the use of acid based patio and brick cleaners. Other natural stone cleaners should be used with care and sufficient tests carried out in an inconspicuous area prior to widespread application.

Frost / Chemical Protection

All natural stone is porous to some degree. A combination of deep frost and absorbed water content can be harmful to the stone. Prevention of this kind of damage is best dealt with by means of sealing the stone to prevent moisture ingress. Rock salt or other salts can be invasive to natural stone. Use of rock salt is likely to shorten the lifespan of the product due to accelerated erosion. If salt or other invasive chemicals are to be used in the proximity we suggest at the very least sealing the stone with a product that is salt resistant and re-applying at the specified intervals, applying the salt sparingly and not in concentrated heaps. In some circumstances it may be worth considering alternative, none natural materials for these areas.

Bingley Stone is a trading name of Bingley Roofing Contractors Ltd
Registered in England and Wales Number 4646898
Vat Registration Number 827 9803 88

Registered Office Cullingworth Mills, Cullingworth, West Yorks BD13 5AB

Telephone +44 (0) 1535 273 813
Facsimile +44 (0) 1535 273 194
Email info@bingleystone.com